

PRODUCT

SKU/Color Names :

AT-02 Mile High	AT-17 Myrtle Beach
AT-03 Venice Beach	AT-18 Islamorada
AT-04 Rehoboth	AT-19 Amelia
AT-05 Antigua	AT-20 Whitehaven
AT-07 Wildwood Crest	AT-21 Blue Sands
AT-12 Oakwood	AT-22 Loredo
AT-13 Cannes	AT-24 Santorini
AT-14 Biscayne	AT-25 Mancora
AT-15 Galway	AT-26 Palomino
AT-16 Brighton	AT-27 Captiva

Construction :

- 4mm Rigid Core (Stone and Virgin DOTP Composite)
- 1mm IXPE attached cushion (No VOCs)
- 5 unique planks per pattern, 10 with a flip

Wear Layer :

20mil with Quantum X™ Technology Finish

Installation:

- Click, Unilin Locking System
- Float or Glue Down
- 50 LF before transition needed
- Matching Accessories: 3-in-1 Molding, Flush Stair Nose
- Use Polyurethane for wet spaces. Pressure sensitive adhesive is acceptable for other areas. Please reference our installation instructions for further details or contact sales@duratousa.com.
- A 50'x50' install requires 10mm expansion space along walls in uncontrolled environments (such as no HVAC).
- Do not install below 50°F, 24-hr acclimation time.
- Use a floor mat for furniture utilizing castor wheels.

SIZE/PACKAGING

Plank Size: 7.2" x 48"

Planks/Carton: 10 Sq. Ft./Carton : 24.028

Cartons/Pallet : 55 Sq. Ft./Pallet : 1,321.54

Ft./Container : 26,430.80

FEATURES



ANTI-MICROBIAL



WATERPROOF



FIRE RESISTANT



PET FRIENDLY



INDENT RESISTANT



LIGHT COMMERCIAL USE
Durable enough to withstand everyday foot traffic.



QUANTUM X™ TECHNOLOGY
Industry-leading resistance to scratches, stains and dents, strengthened by diamonds.

TEST DATA

ASTM E492-09 Impact Sound Conduction & ASTM E90-09 Airborne Sound Conduction

6"slab, no drop ceiling: STC 53 db / IIC 55 db OSB subfloor with fiberglass and open truss using standard resilient channel with fastened gypsum board: STC 58 / IIC 55 / HIIC 66

** Sound test scores are relative to varying conditions. For accurate results, contact Durato for on-site testing and/or specific buildouts.*

ASTM D2394 Slip Resistance DCOF (Sliding)

Wet: Manufacturing Direction 0.63
Wet: Across-Manufacturing Direction 0.72
Dry: Manufacturing Direction 0.58
Dry: Across-Manufacturing Direction 0.60

ASTM D2394 Slip Resistance SCOF (Static)

Wet: Manufacturing Direction 0.72
Wet: Across-Manufacturing Direction 0.78
Dry: Manufacturing Direction 0.59
Dry: Across-Manufacturing Direction 0.70

ASTM D1037 Dynamic Load Limit

1,162 psi

ASTM F970-22 Static Load Limit

Passes, 0.35mm indent, 250 psi

ASTM F1914-18 Residual Indentation

Meets or Exceeds, average 0.09mm

ASTM F2199-20 Dimensional Stability

Meets or Exceeds

ASTM E648 Critical Radiant Flux

Meets or Exceeds, Class 1 (>1.10)

ASTM F1514-19 Resistance to Heat

Meets or Exceeds, average ΔE^* 0.80

ASTM F1515-21 Resistance to Light

Meets or Exceeds, average ΔE^* 1.72

ASTM F925-13 Resistance to Chemicals

No change, Not affected

ASTM C518 Thermal Resistance

R Value -0.6

WARRANTY



LIMITED RESIDENTIAL WARRANTY



LIMITED LIGHT COMMERCIAL WARRANTY

